Aurora Specification



COMPOSITION		
Construction	ISO2424	Tufted 1/12th Loop Pile
Pile Fibre	ISO2076	100% Solution Dyed Nylon
Primary Backing	ISO2424	Non-woven Polyester
Secondary Backing	ISO2424	Bitumen with glass fibre 3kg/m ²
Pile Height	ISO1766	2.5 mm ± 0.5mm
Total Height	ISO1765	5.0 mm ± 0.5mm
Pile Weight	ISO1958	$525 \text{ gr/m}^2 \pm 5\%$
Total Weight	ISO8543	$3590 \text{ gr/m}^2 \pm 10\%$
Pile Density	ISO1763	181,100 tufts/m² ± 5%
Tile Size	EN994	50 x 50 cm
Tiles per Box		20 tiles per box (5m²)
CLASSIFICATION		
Flammability (Fire Spread EN13501)	ISO11925	Fs ≤ 150mm within 20 seconds
Flammability (Radiant Panel EN13501)	ISO9239	C _{fl} -S1
Flammability (Hot Metal Nut)	BS4790	Low radius effects of ignition
Wear Resistance (Castor Chair Test)	ISO4918	Pass ≥ 2.4 (A – Continuous Use)
Electrical Vertical Resistance	ISO10965	Pass $\leq 10^9 \Omega$
Electrostatic Propensity (Stroll Test)	ISO6356	Pass <2.0kV
Slip Resistance	EN13893	DS
Dimensional Stability	EN986	Pass <0.2%
Acoustic Impact Noise Reduction	ISO10140-1	23dB
Sound Absorption	ISO354	500Hz-0.07as, 1000Hz-0.16as,
		2000Hz-0.28as, 4000Hz-0.32as
Colour Fastness – Light (CIELAB)	ISO105	<u>≥</u> 6
Colour Fastness – Rubbing (CIELAB)	ISO105	<u>></u> 5
Colour Fastness – Water (CIELAB)	ISO105	<u>></u> 5
Classification for Use	ISO10874	Class 33 Commercial Heavy
Luxury Class Rating	EN1307	LC1

ENVIRONMENTAL WARRANTY 10 Year Wear Warranty

Formaldehyde Emission HCHO - E1

INSTALLATION





CERTIFICATION













11111













© The Floor Hub. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available on request.

> The Floor Hub HQ & Trade Bar, No 3, 14 Greycaine Road, Watford, Herts. WD24 7GP The Floor Hub Showroom, The Vault, 8-11 St John's Lane, Clerkenwell, London. EC1M 4BF Tel: 01923 211151 Email: hello@thefloorhub.co.uk www.thefloorhub.co.uk