## **Composition Specification**



COMPOSITION		
Construction	ISO2424	Tufted 1/12th Loop Pile
Pile Fibre	ISO2076	100% Solution Dyed Nylon
Primary Backing	ISO2424	Non-woven Polyester
Secondary Backing	ISO2424	Bitumen with glass fibre 3kg/m <sup>2</sup>
Pile Height	ISO1766	3.0 mm ± 0.5mm
Total Height	ISO1765	6.5 mm ± 0.5mm
Pile Weight	ISO1958	$630 \text{ gr/m}^2 \pm 5\%$
Total Weight	ISO8543	4400 gr/m² ± 10%
Pile Density	ISO1763	245,000 tufts/m <sup>2</sup> ± 5%
Tile Size	EN994	50 x 50 cm
Tiles per Box		20 tiles per box (5m²)
CLASSIFICATION		
Flammability (Fire Spread EN13501)	ISO11925	Fs ≤ 150mm within 20 seconds
Flammability (Radiant Panel EN13501)	ISO9239	B <sub>fl</sub> -S1
Flammability (Hot Metal Nut)	BS4790	Low radius effects of ignition
Wear Resistance (Castor Chair Test)	ISO4918	Pass ≥ 2.4 (A – Continuous Use)
<b>Electrical Vertical Resistance</b>	ISO10965	Pass $\leq 10^9 \Omega$
Electrostatic Propensity (Stroll Test)	ISO6356	Pass <2.0kV
Slip Resistance	EN13893	DS
Dimensional Stability	EN986	Pass <0.2%

ISO10140-1

ISO354

ISO105

ISO105

ISO105

ISO10874

EN1307

**Colour Fastness – Light (CIELAB) Colour Fastness – Rubbing (CIELAB)** 

**Acoustic Impact Noise Reduction** 

**Sound Absorption** 

**Luxury Class Rating** 

**CERTIFICATION** 

Colour Fastness – Water (CIELAB) **Classification for Use** 

**ENVIRONMENTAL** 

Formaldehyde Emission HCHO - NA **BREEAM A Rating** 

## **INSTALLATION**

**WARRANTY** 

25dB

<u>></u>7

>4

>4

LC1

500Hz-0.07as, 1000Hz-0.18as, 2000Hz-0.28as, 4000Hz-0.37as

Class 33 Commercial Heavy

10 Year Wear Warranty















MONOLITHIC



**OUARTER TURN** 



BRICK



.... .....













© The Floor Hub. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available on request.