## **Palladium Specification**



COMPOSITION		
Construction	ISO2424	Tufted 1/10th Loop Pile
Pile Fibre	ISO2076	Aqualon 100% PA6 Solution Dyed Nylon
Primary Backing	ISO2424	Non-woven Polyester
Secondary Backing	ISO2424	Bitumen with glass fibre 3kg/m <sup>2</sup>
Pile Height	ISO1766	3.5 mm ± 0.5mm
Total Height	ISO1765	7.2 mm ± 0.5mm
Pile Weight	ISO1958	730 gr/m² ± 5%
Total Weight	ISO8543	4500 gr/m² ± 10%
Pile Density	ISO1763	186,000 tufts/m² ± 5%
Tile Size	EN994	50 x 50 cm
Tiles per Box		20 tiles per box (5m <sup>2</sup> )
CLASSIFICATION		
Flammability (Fire Spread EN13501)	ISO11925	Fs ≤ 150mm within 20 seconds
Flammability (Radiant Panel EN13501)	ISO9239	B <sub>fl</sub> -S1
Flammability (Hot Metal Nut)	BS4790	Low radius effects of ignition
Wear Resistance (Castor Chair Test)	ISO4918	Pass ≥ 2.4 (A – Continuous Use)
Electrical Vertical Resistance	ISO10965	$Pass \leq 10^9 \Omega$
Electrostatic Propensity (Stroll Test)	ISO6356	Pass <2.0kV
Slip Resistance	EN13893	DS
Dimensional Stability	EN986	Pass <0.2%
Acoustic Impact Noise Reduction	ISO717	29dB
Sound Absorption	ISO354	500Hz-0.09as, 1000Hz-0.22as, 2000Hz-0.34as, 4000Hz-0.42as
Colour Fastness – Light (CIELAB)	ISO105	<u>≥</u> 7
Colour Fastness – Rubbing (CIELAB)	ISO105	<u>&gt;</u> 4
Colour Fastness – Water (CIELAB)	ISO105	<u>&gt;</u> 4
Classification for Use	ISO10874	Class 33 Commercial Heavy
Luxury Class Rating	EN1307	LC2
ENVIRONMENTAL		WARRANTY
BREEAM A Rating	_	10 Year Wear Warranty
CERTIFICATION		INSTALLATION
	BREEAM	MONOLITHIC BRICK QUARTER TURN

© The Floor Hub. Specifications are subject to normal manufacturing tolerances and may be changed without prior notice. Copies of actual test results are available on request. The Floor Hub HQ & Trade Bar, No 3, 14 Greycaine Road, Watford, Herts. WD24 7GP The Floor Hub Showroom, The Vault, 8-11 St John's Lane, Clerkenwell, London. EC1M 4BF Tel: 01923 211151 Email: hello@thefloorhub.co.uk

www.thefloorhub.co.uk